(1)

AD 744493

EXPLORATORY DEVELOPMENT TO STUDY GRAPHITE VAPORIZATION KINETICS AND THERMODYNAMICS USING THE MODULATED BEAM MASS SPECTROMETER

GTLy Rept 3 - AD 744494

Quarterly Report No. 1

1 May 1971 to 31 July 1971

Contract No. F33615-71-C-1509 NEW

AVSD-0022-72-CR

For

Air Force Materials Laboratory
Air Force Systems Command
Wright-Patterson Air Force Base, Ohio

Prepared by

AVCO CORPORATION
Systems Division
Lowell Industrial Park
Lowell, Massachusetts 01851

22

Unclassified

Security Classification

DOCUMENT CONTROL DATA R&D

(Security classification of title, body of abstract and indexing annotation must be entered when the overall report is classified)

1 ORIGINATING ACTIVITY (Corporate author)	2a REPORT SECURITY CLASSIFICATION
Avco Corporation Systems Division Lowell, Massachusetts 01851	Unclassified 2b GROUP

3. REPORT TITLE

Exploratory Development to Study Graphite Vaporization Kinetics and Thermodynamics Using the Modulated Beam Mass Spectrometer

4 DESCRIPTIVE NOTES *(Type of report and inclusive dates)*

Quarterly Report No. 1

5 AUTHOR(S) *(Last name, first name, initial)*

Steele, Warren C.
Bourgelas, Frederick N.

6 REPORT DATE	7a TOTAL NO OF PAGES	7b NO. OF REFS
	16	3

8a CONTRACT OR GRANT NO	9a ORIGINATOR'S REPORT NUMBER(S)
F33615-71-C-1509 b PROJECT NO	Qtrly. Rep. No. 1 AVSD-0022-72-CR
c d	9b OTHER REPORT NO(S) *(Any other numbers that may be assigned this report)*

10 AVAILABILITY/LIMITATION NOTICES

Approved for public release; distribution unlimited.

11 SUPPLEMENTARY NOTES	12 SPONSORING MILITARY ACTIVITY
	Air Force Materials Laboratory Air Force Systems Command Wright-Patterson Air Force Base, Ohio

13 ABSTRACT

Progress is reported in a program of mass spectrometric studies of graphite vaporization kinetics. Emphasis has been placed on measurement of reflection coefficients for the three major constituents of carbon vapor impinging on a heated graphite surface. Use of modulation techniques has been employed to detect a reflected beam interacting with the graphite surface to $T_s \leq 2600°K$. Development of a vapor source for an isotopically enriched carbon beam using graphite powder is described.

I

DD FORM 1 JAN 64 1473

Unclassified

Security Classification

Unclassified

Security Classification

14 KEY WORDS	LINK A		LINK B		LINK C	
	ROLE	WT	ROLE	WT	ROLE	WT
Vaporization kinetics						
Graphite						
Molecular beam						
Mass spectrometer						

INSTRUCTIONS

1. ORIGINATING ACTIVITY: Enter the name and address of the contractor, subcontractor, grantee, Department of Defense activity or other organization *(corporate author)* issuing the report.

2a. REPORT SECURITY CLASSIFICATION: Enter the overall security classification of the report. Indicate whether "Restricted Data" is included. Marking is to be in accordance with appropriate security regulations.

2b. GROUP: Automatic downgrading is specified in DoD Directive 5200.10 and Armed Forces Industrial Manual. Enter the group number. Also, when applicable, show that optional markings have been used for Group 3 and Group 4 as authorized.

3. REPORT TITLE: Enter the complete report title in all capital letters. Titles in all cases should be unclassified. If a meaningful title cannot be selected without classification, show title classification in all capitals in parenthesis immediately following the title.

4. DESCRIPTIVE NOTES: If appropriate, enter the type of report, e.g., interim, progress, summary, annual, or final. Give the inclusive dates when a specific reporting period is covered.

5. AUTHOR(S): Enter the name(s) of author(s) as shown on or in the report. Enter last name, first name, middle initial. If military, show rank and branch of service. The name of the principal author is an absolute minimum requirement.

6. REPORT DATE: Enter the date of the report as day, month, year; or month, year. If more than one date appears on the report, use date of publication.

7a. TOTAL NUMBER OF PAGES: The total page count should follow normal pagination procedures, i.e., enter the number of pages containing information.

7b. NUMBER OF REFERENCES: Enter the total number of references cited in the report.

8a. CONTRACT OR GRANT NUMBER: If appropriate, enter the applicable number of the contract or grant under which the report was written.

8b, 8c, & 8d. PROJECT NUMBER: Enter the appropriate military department identification, such as project number, subproject number, system numbers, task number, etc.

9a. ORIGINATOR'S REPORT NUMBER(S): Enter the official report number by which the document will be identified and controlled by the originating activity. This number must be unique to this report.

9b. OTHER REPORT NUMBER(S): If the report has been assigned any other report numbers *(either by the originator or by the sponsor)*, also enter this number(s).

10. AVAILABILITY/LIMITATION NOTICES: Enter any limitations on further dissemination of the report, other than those imposed by security classification, using standard statements such as:

(1) "Qualified requesters may obtain copies of this report from DDC."

(2) "Foreign announcement and dissemination of this report by DDC is not authorized."

(3) "U. S. Government agencies may obtain copies of this report directly from DDC. Other qualified DDC users shall request through _____."

(4) "U. S. military agencies may obtain copies of this report directly from DDC. Other qualified users shall request through _____."

(5) "All distribution of this report is controlled. Qualified DDC users shall request through _____."

If the report has been furnished to the Office of Technical Services, Department of Commerce, for sale to the public, indicate this fact and enter the price, if known.

11. SUPPLEMENTARY NOTES: Use for additional explanatory notes.

12. SPONSORING MILITARY ACTIVITY: Enter the name of the departmental project office or laboratory sponsoring *(paying for)* the research and development. Include address.

13. ABSTRACT: Enter an abstract giving a brief and factual summary of the document indicative of the report, even though it may also appear elsewhere in the body of the technical report. If additional space is required, a continuation sheet shall be attached.

It is highly desirable that the abstract of classified reports be unclassified. Each paragraph of the abstract shall end with an indication of the military security classification of the information in the paragraph, represented as *(TS), (S), (C), or (U)*

There is no limitation on the length of the abstract. However, the suggested length is from 150 to 225 words.

14. KEY WORDS: Key words are technically meaningful terms or short phrases that characterize a report and may be used as index entries for cataloging the report. Key words must be selected so that no security classification is required. Identifiers, such as equipment model designation, trade name, military project code name, geographic location, may be used as key words but will be followed by an indication of technical context. The assignment of links, rules, and weights is optional.

TL

Unclassified

Security Classification

TABLE OF CONTENTS

ABSTRACT

I. INTRODUCTION. 1

II. MODULATED BEAM EXPERIMENTS. 3

III. THE MASS SPECTRUM OF C_3 10

IV. INSTRUMENTAL DEVELOPMENTS 11

A. New Carbon Vapor Source 11

B. Rotatable Target Holder 12

V. CONCLUSIONS AND FUTURE PLANS. 14

VI. REFERENCES. 16

III

LIST OF ILLUSTRATIONS

Figure No.		
1	Schematic Diagram of Avco's Pulsed Molecular Beam Mass Spectrometer.	4
2	C_3 Reflection from Polycrystalline Graphite	5
3	Carbon Atom Reflection.	7
8	C_3 Reflection	8

LIST OF TABLES

Table No.		
I	Mass Spectrum of C_3	10

ABSTRACT

Progress is reported in a program of mass spectrometric studies of graphite vaporization kinetics. Emphasis has been placed on measurement of reflection coefficients for the three major constituents of carbon vapor impinging on a heated graphite surface. Use of modulation techniques has been employed to detect a reflected beam interacting with the graphite surface to $T_s \leq 2600^{\circ}K$. Development of a vapor source for an isotopically enriched carbon beam using graphite powder is described.

IV

I. INTRODUCTION

As a prime candidate material for advanced re-entry vehicle applications, graphite appears particularly attractive for use when severe re-entry trajectories require survival under extreme conditions. In order to make the required calculations of recession rate, designers of graphitic components of such systems require a knowledge of the vaporization kinetics and thermochemistry of graphite. Experimental data on this subject has been limited, being confined mainly to studies of equilibrium vaporization below the temperature of 2800°K. Although other aspects of graphite vaporization have received some attention, design data must still be obtained in part by extrapolation, estimation and theoretical calculation. The present program was designed to provide experimental answers in several of the outstanding problem areas. These include measurement of condensation and reflection coefficients for carbon vapor at graphite surfaces and determination of the polymeric composition of carbon vapor produced by free evaporation from a graphite surface.

In response to the need for better, more advanced methods for the study of gas-surface interactions, Avco developed for the Air Force Materials Laboratory, a modulated beam mass spectrometer apparatus.[1] This unique apparatus allows reactions between a heated solid material and discrete pulses of the gas. Vaporizing reaction products are analyzed individually by the mass spectrometer. By synchronizing the spectrometer detection system to the vapor beam modulator, the periodic time-intensity waveform of the gaseous reaction products can be constructed, providing important information on the kinetics of the reaction under observation.

This apparatus is now being applied to studies of graphite-carbon vapor interactions, an induction heated graphite cylinder providing a carbon vapor beam which impinges on a resistively heated graphite target.

During this quarterly reporting period emphasis has been placed on the study of tne condensation/reflection reactions using the beam modulation techniques. In the following sections progress is reported in extending reflection measurements to higher target temperatures. By using beam modulation we have succeeded in operating at target temperatures at which target vaporization obscures the reflected beam from observation in steady-state operation. Development of a new beam source capable of sustained operation using graphite powder has been achieved, paving the way to experimental use of isotopically enriched C^{13} graphite powder and plans for a rotatable target holder are described.

II. MODULATED BEAM EXPERIMENTS

Direct observation of carbon vapor reflection by graphite surfaces is limited to the single study by Chupka, Berkowitz, Meschi and Tasman.[2] In 1962 they reported the results on an experiment in which a mass spectrometer was used to detect carbon vapor reflected from a graphite filament. Two parallel 0.020 inch graphite filaments were suspended under the ion source of a mass spectrometer in such a way that only one filament was "visible" via a line-of-sight path to the ionizer. A portion of the atoms or molecules vaporized or reflected from this filament could be analyzed and detected by the mass spectrometer. Measurements were made to compare ion intensities of each species produced by direct evaporation from the visible filament with those produced by evaporation from the other filament and reflection from the surface of the visible filament. Values for a reflection coefficient α_r (number reflected/number impinging) were calculated assuming a random distribution for the reflected beam. Results were reported for C_1 and C_3 only, and for only two values of the temperature of the reflecting surface. These interesting observations gave: for C_1, $\alpha_r = 0.3$ ($T = 800^\circ K$) and $\alpha_r = 0.6$ ($T = 2300^\circ K$); for C_3, $\alpha_r = 1.1$ ($T = 800^\circ K$) and $\alpha_r = 0.9$ ($T = 2300^\circ K$).

Recently we have adopted our modulated beam mass spectrometer to a study of carbon vapor reflection.[3] Operating primarily without beam chopping we have verified qualitatively the results of Chupka, et al, and have greatly extended their study by including C_2 and by providing a continuous record of reflection as a function of target temperatures in the region $3000^\circ K < T_s < 2100^\circ K$. These results are depicted in Figure 2.



Figure 1. SCHEMATIC DIAGRAM OF AVCO'S PULSED MOLECULAR BEAM MASS SPECTROMETER



71-446

Figure 2. C_3 REFLECTION FROM POLYCRYSTALLINE GRAPHITE

The upper temperature limit of 2100°K was imposed by target vaporization which obscured the reflected beam above this point. However, the region above 2100°K is of particular interest since here the surface temperature approaches the beam temperature and chemical interaction between beam molecules and surface atoms is most likely to occur.

In order to extend our measurements to $T_S > 2100°K$, we have used beam modulation to provide discrimination between the reflected beam (modulated) and the vaporizing surface (non-modulated). The apparatus is then used as depicted in Figure 1 and also with a Princeton Applied Research Corp lock-in amplifier (Model JB-5) replacing the digital signal averager. We have chosen to operate at a chopping frequency of about 40 cycles per second with the beam source operated at near 2700°K. Typical results are shown in Figures 3 and 4.

Intensity of the reflected C_3 beam is seen to continue to decrease slightly with increasing surface temperature to 2600°K. The intensity of the reflected carbon atom beam increases as T_S increases to 2600°K. Pulse shapes as obtained on the digital signal averager continue to faithfully reproduce the chopper profile, showing no observable surface residence time for the vapor beam. These results show a continuation of the trends previously observed at lower temperatures.[3]

Above 2600°K (T_S) the situation changes dramatically. The lock-in amplifier output becomes wildly erratic and the digital signal averager is no longer able to construct a satisfactory waveform. The reason for this behavior is not clear. As this upper temperature limit is approached the signal to noise ratio approaches 10^{-3}, a level which should not incapacitate our signal extracting system. The effect is reproducible



Figure 3. Carbon Atom Reflection



Figure 4. C_g Reflection

and does not seem to be dependent on the absolute level of ion current reaching the mass spectrometer detector. If the explanation lies elsewhere, then one can speculate that an interaction between gas and surface may become increasingly important for high T_s. In order to further investigate this possibility, we are preparing for experiments using an isotopically labeled vapor beam to help separate the reflected beam from surface vaporization and to identify any reaction products of a chemical combination or exchange reaction.

III. THE MASS SPECTRUM OF C_3

The selective reflection of C_3 (vs. C_2 and C_1) by graphite surfaces heated to about 1000°K (see Figure 2), affords an unusual opportunity to observe this species in relative isolation. The mass spectrum of C_3 is of special interest to the high temperature chemist interested in the composition of carbon vapor over hot graphite, since electron impact fragmentation of C_3 may affect the measured ion current due to C_2^+ and C_1^+ if the ionizing voltage is too high. Therefore, we have performed a simple experiment in which the ion currents at masses 12, 24 and 36 were recorded at 100 eV for the reflected carbon vapor beam at constant beam intensity and reflecting surface temperature (T_s = 1000°K). Results are then corrected for contributions from atomic or diatomic vapor species by estimating the maximum possible contribution from the measurements performed at 17 eV and their known appearance potential curves.[3] The resulting net spectrum of C_3 is shown in Table I.

TABLE I

MASS SPECTRUM OF C_3

m/e	ion	rel. int.
36	C_3^+	100.
24	C_2^+	2.1
12	C^+	2.9

The effect of electron impact fragmentation is readily observable in our reflection measurements (Figure 2). At 20 eV the C_1 (atom) curve follows the course outlined while at 25 eV a large fragmentation contribution causes the C_1^+ (mass 12) curve to behave in the manner of C_3.

IV. INSTRUMENTAL DEVELOPMENTS

A. Several improvements or developments in our experimental technique are necessary as preparation for future experiments aimed at extending our knowledge of the carbon vapor-graphite interaction. The first of these involves development of a vapor source to provide a beam of carbon vapor enriched in the ^{13}C isotope. Previous vapor sources providing our normal isotopic beam were fashioned from solid graphite rod encased in a tantalum sleeve. This provides a 0.1 inch diameter graphite surface from which a beam of carbon vapor of sufficient intensity is obtained by heating to 2700°K. The isotopically enriched graphite is available only as a fine-grained powder, and our experience has been that it is not possible to compact this powder into a useful rod without the addition of a binder material.

Inclusion of a foreign material would be most undesirable, so we have sought a different solution. Our first attempts to construct a carbon vapor source from tantalum foil and graphite powder failed. This resistively heated tube furnace regularly "burned out" in the high temperature regions of interest to us. This led to our efforts to compact a rod from the graphite powder, but the rods were also of insufficient quality to withstand the high temperatures.

The final solution consists of using the same tantalum tube used as the sleeve in our other sources. One end of this tube is crimped to produce a very narrow slit 0.15 inches high. The tube is filled with graphite powder and set on a base of graphite rod. This source is heated by RF induction with the graphite rod base slightly below the RF coil. An intense carbon vapor beam is produced by heating to the 2700°K region,

with the intensity and useful lifetime perhaps even surpassing that of the original source made of rod only. We are now testing this with C^{13} powder.

B. A second development concerns the assembly of a rotatable target holder. Our calculation of the reflection coefficient from experimental determinations of reflected beam intensity must include some assumption of the angular distribution of the reflected beam. We have made the simple assumption of a cosine distribution, but specular reflection cannot be ruled out. Therefore, it is very desirable that a direct measurement of the angular distribution be made. The most complete measurement of this quantity would require an apparatus in which the angle of beam incidence to the target and the angle of detection of the reflected beam could be varied independently through a wide range of angles. As presently constituted, our apparatus has both angles fixed (at 45°), and modification to permit independent variation of both angles would be an undertaking much larger than can be justified for present purposes. A much simpler solution lies in using only a rotatable target holder. With source and detector in fixed positions (Figure 1) a rotation of the target through an angle of θ to produce an angle of incidence of $45^{\circ}-\theta$ will permit detection only at the angle $45^{\circ} + \theta$. Even with this restriction a satisfactory estimation of the angular reflection distribution can be obtained. A rotatable target holder is now being assembled.

A rotary vacuum feed-through similar to that used by Varian in their rotary sample manipulator is available. Special problems of high electrical heating currents (up to 150 amps) and water-cooled electrodes

as sample holders are being met through the use of flexible stainless steel bellows to carry both the heating current and the cooling water. Another bellows will be used to permit motion along the z-axis as well. We expect to complete assembly of this device during the next quarter.

V. CONCLUSIONS AND FUTURE PLANS

During this quarter we have successfully extended our measurement of carbon vapor reflection by graphite to higher target surface temperatures. Earlier reflectance measurements using a constant vapor beam were limited to target temperatures below that which produces significant target vaporization ($T_S \lesssim 2100^{\circ}K$). In order to extend this measurement to the vaporizing region which is typical of the practical situation ($T_S \approx T_B$), beam modulation techniques have been adopted. Use of this method has resulted in extension of the maximum target surface temperature several hundred degrees higher, but fails as T_S approaches T_B. In the newly explored regions for T_S, the modulated beam measurements have shown C_3 to be completely reflected, as is the case for all values of T_S above $1100^{\circ}K$. The reflected beam intensity for monatomic carbon continues to increase with increasing surface temperature to the maximum value of T_S attained.

In the preceding sections we have also described development of a carbon vapor beam source utilizing graphite powder as a carbon vapor source. This new source is suitable for use with our isotopically enriched graphite powder. In the next quarter we plan to initiate experiments with the C^{13} source. This will permit us to study the reflection of C_3 at $T_S \gtrsim T_B$ with a minimum of interference from directly vaporized C_3. Careful attention to the isotopic composition of all vaporized and/or reflected species will provide direct evidence on the chemical nature of the reflection/condensation interaction of carbon vapor and solid graphite. Further attention will be given to completion of the rotating target holder. Knowledge of the angular distribution

of reflected molecular beams is crucial to calculation of the reflection coefficient.

VI. REFERENCES

1. Steele, W.C., Technical Report AFML-TR-65-343, Part III (April 1968).

2. Chupka, W.A., J. Berkowitz, D.J. Meschi and H.A. Tasman, in Advances in Mass Spectrometry, Vol. 2, p. 99, MacMillan, New York (1963).

3. Steele, W.C., and F.N. Bourgelas, Technical Report, AFML-TR-71-77 (May 1971).